

Ancamine 2390

Rapid thin film set. High tear resistance and tensile strength, and moderate elongation. Good chemical and moisture resistance

Higher
Flexibility



Faster cure at
ambient and low T

Ancamine 2803

>100% elongation without adding diluents or flexibilizer. Good compressive strength. Fast Cure

For Use with Part A

Ancarez 2364

Reactive flexibilizer to use with epoxy resin on "A" side. Provides versatility in formulations by varying components ratio and choice of curing agent

Joint Fillers

Used for construction joints or to fill in cracks in concrete floors and slabs

- A semi-rigid filled epoxy can prevent concrete deterioration at the edge of the joint or crack
- Typical requirements:
 - 40-100% elongation
 - >50 shore D hardness
 - Lower modulus to accommodate potential expansion and contraction