

Product Recommendation for Epoxy Resins

TECHNOLOGY	CURING AGENT	BENEFITS											APPLICATIONS														
		LOW VISCOSITY	LONG POTLIFE (@25 C)	CARBAMATION RESISTANCE	FAST RETURN TO SERVICE/ EARLY WALK-ON	AESTHETICS ²	ADHESION CONCRETE	MECHANICAL RESISTANCE	FLEXIBILITY	CHEMICAL RESISTANCE	LOW EMISSIONS	WATER VAPOUR PERMEABILITY	TEMPERATURE RESISTANCE	LOWER BINDER COST	PRIMER	CONCRETE REINFORCEMENT	PAINT/TOPCOAT	TRANSPARENT SEALER/TOPCOAT	SECONDARY CONTAINMENT/ PARK DECK FLOORING	SELF-LEVELLER FLOOR (SLF)	ESD FLOORING	SCREEDS AND MORTARS	CRACK INJECTION	CHEMICAL BOLD ANCHORING	STRUCTURAL ADHESIVE	PIPE REHABILITATION/ CIPP	
Waterborne Epoxy	Anquamine® 287	++		++	++		+++	+	+	++		+++		+++								+++	++				
	Anquamine 721	+	++	++		++	+++					+++	+	+++	+	+++	+										
	Anquamine 735	+		++	++		++	+				+++	+++	++	+++				+++	+	++						
Solvent-free Epoxy	Anquawhite™ 100	++	+++	++		++	+++		+	+++	+	+				+++	+++										
	Ancamide® 3200		++				++		+					++	+										+		
	Ancamide 3444		+		+		++							++	+										+		
	Ancamide 3419	++	+++				++						++													+++	
	Ancamine 2143		++	+						+++						++			+++	++							
	Ancamine 2432		+		+++		++	++		+++				+		++			+++	++	++	++	+	+++	++		
	Ancamine 2692		++		+++		++			+++				++	+++							++					
	Ancamine 2719				+++		++	++		+++					++				++	+	++	++	+++	+++			
	Ancamine 2712M			++	++		++	+++		+++		+		++		+				+		++		++	++		
	Ancamine 2739		++	++	+	+		+++		++	+++					+++	++		+++								
	Ancamine 2759			++	++			+		++				++		++			++		+						
	Ancamine 2760		++	+		+		+						++		+++	++		++		++						
	Ancamine 2806			++		+++	+++			+++						+++	++						++				
	Ancamine 3215	++			++	+										++	++			++		+++					
	Ancamine 3456								+++	++						++				++				+	++		
	Poly-carbamide	Amicure® IC-321 ¹	++	+	+++	+	+++		+++	+	++					++	+++			+							
Amicure IC-221 ¹		++		+++	++	+++		++	+	++					++	+++			+								

+++ Excellent ++ Highly Recommended + Recommended

Notes: All products listed are free from phenol, alkyl phenols, tert-butyl phenol, Bisphenol-A, Bisphenol F. Other products are available on requests. Product comparisons are made within same the technology group.

¹ Amine curing agent for isocyanate resin ² Aesthetics is defined as a combination of UV resistance and/or pigment compatibility and gloss

EVONIK INDUSTRIES AG
7201 Hamilton Boulevard
Allentown, PA 18195-1501
cheminfo@evonik.com
www.evonik.com

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.

