

ANCAMIDE® 351A Curing Agent**DESCRIPTION**

Ancamide 351A curing agent is a member of a new series of reactive polyamides developed for use in the curing of epoxy resins in coatings and adhesives applications. Special features include good color, color stability, excellent corrosion resistance and superior adhesion properties. Ancamide 351A is freely compatible with a wide range of solvents, including those generally used in epoxy resin based coatings.

ADVANTAGES

- Good corrosion resistance
- Excellent adhesion to a variety of substrates
- Good color and light stability
- Compatible with wide range of solvents

APPLICATIONS

- Structural adhesives
- Solvent based marine and protective coatings
- Primers, sealers and coatings for concrete

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers. Do not freeze

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 351A curing agent

TABLE 1: TYPICAL PROPERTIES

Appearance	Clear amber liquid
Color (Gardner)	8 max
Viscosity² @ 25°C, (mPa.s)	10,000 - 20,000
Amine Value³, (mg KOH/g)	344
Specific Gravity @ 21°C	0.97
Equivalent Wt (active N-H)	100
Recommended use Level⁴, (phr)	50-55
Solids Content, (%)	100

TABLE 2: TYPICAL HANDLING PROPERTIES (@ 50 PHR)

Gel Time⁵ (mins)	150
Thin Film Set Time @ 25 °C, (h)	10

TABLE 3: TYPICAL CURE SCHEDULE

(i) 2-7 Days at Room Temperature

TABLE 4: FILM PROPERTIES AFTER 10 DAYS CURE @ 23°C

Direct impact (cm.kg)	150
Reverse impact (cm.kg)	10
Flexibility Cylindrical Mandrel⁷ (mm pass)	3

(1) ASTM D 1544-80

(2) Brookfield RVTD, Spindle 4

(3) Perchloric Acid Titration

(4) Theoretical value with Bisphenol A diglycidyl ether (EEW=190)

(5) 150 gms mixed mass @ 25°C

(6) BK Drying Recorder Phase II

(7) Erichsen mandrel tester 266

SUPPLEMENTARY INFORMATION

STRUCTURAL ADHESIVES APPLICATIONS

Ancamide 351A curing agent is medium viscosity polyamide, supplied at 100% solids. The product is intended for use in combination with or without other amine curing agent in two part room temperature or heat cured adhesives formulations. When used with a standard DGEBA type liquid epoxy resin (EEW=190), Ancamide 351A curing agent offers excellent handling and physical properties and adhesion to various substrates.

Ancamide 351A curing agent has a non-critical loading and can be used at levels ranging from 40 to 70 phr with the preferred range being 50-60 phr with a standard DGEBA type liquid epoxy resin.

PHYSICAL PROPERTIES

Physical properties of Ancamide 351A curing agent cured standard liquid epoxy resin was compared with Ancamide 350A cured epoxy after seven days ambient temperature cure and after a 30 minutes cure @120 °C. The tensile data after seven days ambient cure schedule shows that Ancamide 351A curing agent cured epoxy resin offers greater than 30% higher tensile strength and greater than 80% higher tensile elongation without any adverse effect on tensile modulus. This behavior indicates that Ancamide 351A curing agent **provides inherent toughness to the cured epoxy resin.**

The tensile data after heat cure schedule shows that Ancamide 351A curing agent demonstrated more than 25% increase in tensile elongation as compared to Ancamide 350A without any adverse impact on tensile strength. In addition, increased elongation is observed without significant reduction in glass transition temperature.

TABLE 5: PHYSICAL PROPERTIES

	Ancamide 351A	Ancamide 350A
DGEBA liquid epoxy resin	100	100
Ancamide 350A	0	55
Ancamide 351A curing agent	55	0
<i>After 7 Days RT Cure</i>		
Tensile Strength, N/mm ²	59.3	44.1
Tensile elongation at failure, %	3.4	1.8
Tensile Modulus, kN/mm ²	2.84	2.81
T _g , C	50	50
<i>After 30 minutes at 120°C Cure</i>		
Tensile Strength, N/mm ²	57.2	58.6
Tensile elongation at failure, %	7.0	5.5
Tensile Modulus, kN/mm ²	2.36	2.51
T _g , C	96	100

STARTING POINT FORMULATION

A two-part model formulation (Appendix 1) was prepared using Ancamide 351A curing agent as a main curative. An aliphatic amine was used as a co-curing agent along with Ancamide 351A curing agent. Typical fillers and additives were used in the same formulation. A control formulation was prepared using Ancamide 350A.

Epoxy portion and a curative portion were mixed together based on theoretical EEW of epoxy portion and AHEW of a curative using 1:1 stoichiometric ratio. The mixed adhesive system was used to make single lap shear samples and peel samples for further testing.

Substrates used were cold rolled steel (CRS), ABS and polycarbonate. All substrates were used without any surface treatment prior to bonding.

For CRS lap shear samples, 0.5" overlap was used. For ABS and polycarbonate substrates, 1.0" overlap was used. Only the CRS substrate was used to prepare peel samples. In all cases, 10 mils bondline thickness was maintained using 10 mils diameter glass beads.

All samples were cured following two cure schedules: (1) seven days ambient temperature cure or (2) 30 minutes at 120°C cure. The samples were tested at ambient temperature following standard test methods.

PERFORMANCE EVALUATION

TABLE 6: SHEAR AND PEEL STRENGTH

	"B" Component	
	Ancamide 351A	Control (Ancamide 350A)
<i>7 days at 25°C cure</i>		
CRS/CRS shear strength, N/mm ²	12.4	11.7
ABS/ABS shear strength, N/mm ²	3.6	2.5
Polycarbonate/Polycarbonate Shear strength, N/mm ²	1.6	1.7
CRS/CRS peel strength, N/m	1837	1715
<i>30 minutes at 120°C cure</i>		
CRS/CRS shear strength, N/mm ²	13.8	14.1
CRS/CRS peel strength, N/m	2450	2362

LAP SHEAR STRENGTH

After room temp cure and after heat cure schedules, formulation based on Ancamide 351A curing agent demonstrated performance that was slightly improved versus the Ancamide 350A based formulation. The mode of failure for CRS was 100% cohesive and adhesive for thermoplastic substrates.

PEEL STRENGTH

After both cure schedules, Ancamide 351A curing agent based formulation exhibited higher peel strength compared to the Ancamide 350A based formulation. In both cases, the mode of failure was cohesive.

SOLVENT BASED MARINE & PROTECTIVE COATINGS APPLICATION

FILM PROPERTIES

In a clear coat formulation Ancamide 351A curing agent exhibits a good degree of flexibility. As shown in Table 3, the direct impact resistance of Ancamide 351A curing agent is comparable to Ancamide 350A. Ancamide 351A curing agent formulations can also be accelerated using Ancamine® K54 accelerator. Levels can be varied to achieve the desired dry speed properties, with the preferred level in the 2.5-5.0% range based on Ancamide 351A curing agent use level.

Property	Ancamide 351A(*)	Ancamide 350A(*)
Direct Impact	40	40
Reverse Impact	10	10
Dry Speed BK Phase II (h)	9:30	10:00
Dry Speed (+2.5% K54)	5:00	5:30
Specular Gloss 60°	90	95
Cross Hatch Adhesion (dry)	Gt0	Gt0

(*) Ancamide 351A curing agent and Ancamide 350A tested with liquid Bis A diglycidyl ether (EEW 190, Cross hatch adhesion Gt0 = no loss of adhesion.)

STARTING POINT FORMULATIONS

Appendix 2 contains an anti-corrosive primer formulation based on Ancamide 351A curing agent. As with all solvent based coatings, dry times are influenced by solvent choice -- dry times will vary depending upon the ratio of polar and non-polar solvents incorporated into the coating formulation. Pot lives as measured by the time for the mix to double in viscosity are in the 3-6 hours range, which is typical for such solvent based polyamide systems.

Formulation A351A-1, with Liquid Epoxy Resin, is 64% volume solids. PVC is 35% for both formulations. The primer formulation is compatible with a variety of different let down solvents (including xylene, n-butanol, MIBK, methoxypropanol, etc) and can be further let down if required for additional spray applications. The coating formulation can be applied with conventional spray equipment or brush applied to the steel substrate.

Formulation A351A-1 was evaluated for corrosion resistance properties using salt spray, distilled water immersion and NaCl 3.5% immersion at room temperature. After 1000 hrs exposure, coatings exhibit excellent corrosion resistance. No signs of field blisters were detected using the above tests, with panels exhibiting no scribe creep in the salt spray test. For comparative purposes, Ancamide 350A was also included in the test study as the "industry" standard reference. In all corrosion resistance tests conducted, both Ancamide 351A curing agent and Ancamide 350A demonstrated comparable performance.

PERFORMANCE EVALUATION

Formulation A351A-1 was evaluated in 5% salt spray, distilled water immersion at room temperature and NaCl 3.5% immersion at room temperature, following a 10 day ambient cure of applied coatings.

Coatings were applied to grit blasted, hot rolled steel (SA2.5), using conventional spray equipment, in double coats to give coatings with a 75-100 μ (3-4 mils) dry film thickness (DFT). In salt spray, (ASTM B-117) panels were scribed and evaluated for field blisters using the US Federal Standard Test Method 141a, Method 6461 and the scribe creep was rated in accordance with ASTM D-1654. Similar evaluations were made for panels placed in NaCl 3.5% immersion at room temperature and distilled water immersion. Panels exposed to distilled water immersion were not scribed and coatings were assessed for blistering only. These tests also included evaluations for changes in visual appearance.

CORROSION RESISTANCE

Anti-corrosive primers based on Ancamide 351A curing agent and Ancamide 350A, were evaluated for salt spray, distilled water and NaCl 3.5% immersion at room temperature. The results obtained are presented in Table 6, 7 and 8 on the following page. After 1000 h salt fog exposure, formulations with Ancamide 351A curing agent exhibit excellent resistance comparing favorably to that of Ancamide 350A. Both formulations also demonstrated excellent water and salt water resistance with no signs of field blistering being observed following 1,000 h continuous testing.

TABLE 6: SALT SPRAY RESISTANCE – ANCAMIDE 351A & ANCAMIDE 350A CURING AGENTS (1000H)

	Ancamide 351A Curing Agent	Ancamide 350A
Overall rating	9 – 10	9 – 10
Scribe creep	0 – 1 mm	0 – 1 mm
Cross hatch adhesion after 1,000 hours	5B	5B

TABLE 7: DISTILLED WATER IMMERSION AT RT - ANCAMIDE 351A & ANCAMIDE 350A CURING AGENTS (1000 H)

	Ancamide 351A Curing Agent		Ancamide 350A	
	Before immersion	After 1,000 hours	Before immersion	After 1,000 hours
Cross hatch adhesion	5B	5B	5B	5B
Gloss/Appearance	No change	No change	No change	No change

TABLE 8: NACL 3.5% IMMERSION AT RT – ANCAMIDE 351A & ANCAMIDE 350A CURING AGENTS

	Ancamide 351A Curing Agent		Ancamide 350A	
	Before immersion	After 1,000 hours	Before immersion	After 1,000 hours
Cross hatch adhesion	5B	5B	5B	5B
Gloss/Appearance	No change	No change	No change	No change
Scribe creep	0 mm	0 mm	0 mm	0 mm

SALT SPRAY PANELS 1000 H EXPOSURE

NACL 3.5% IMMERSION AT ROOM TEMPERATURE 1000 H EXPOSURE



Ancamide 350A



Ancamide 351A curing agent



Ancamide 350A



Ancamide 351A curing agent

APPENDIX 1

TABLE 9: ANCAMIDE 351A CURING AGENT: TWO-PART ADHESIVE FORMULATION

A-Component (g)			
1. Epoxy resin	DER 331	Dow Chemicals	60
2. Filler	Microtuff AG 445	Speciality Minerals	38
3. Additive	Cab-O-Sil TS 720 ¹	Cabot Industries	2
Total A			100

A-Component Manufacture Procedure:

- Charge components 1-3 and stir homogeneous at medium to high shear

B-Component (g) Control			
1. Curing agent	Ancamide 350A	Evonik	40
2. Curing agent	Modified Aliphatic	Evonik	10
3. Filler	Microtuff AG 445	Speciality Minerals	22
4. Filler	Toyol 101 Aluminium powder	Toyol- America	27
5. Additive	Cab-O-Sil TS 720 ¹	Cabot Industries	1
Total B			100

B-Component (g) Ancamide 351A curing agent			
1. Curing agent	Ancamide 351A curing agent	Evonik	40
2. Curing agent	Modified Aliphatic	Evonik	10
3. Filler	Microtuff AG 445	Speciality Minerals	22
4. Filler	Toyol 101 Aluminium powder	Toyol-America	27
5. Additive	Cab-O-Sil TS 720 ¹	Cabot industries	1
Total B			100

B-Component Manufacture Procedure:

- Charge components 1-5 and stir homogeneous at medium to high shear

(1) Aerosil R202 by Evonik may also be used

TABLE 10: TECHNICAL DATA

EEW of A Component	317
EEW of B Components	201
Mixing ratio (by weight)	100 of A : 63 of B
Solid content wt. (%)	100

APPENDIX 2

TABLE 11: FORMULATION A351-1: ANCAMIDE 351A CURING AGENT ANTI- CORROSIVE PRIMER FORMULATION

A-Component (g)			Anti-Corrosive Primer
1. Epoxy Resin	DER 331	Dow	229.40
2. Epodil® LV5 diluent	Epodil® LV5 diluent	Evonik	22.90
3. Epodil® 748 reactive diluent	Epodil® 748 reactive diluent	Evonik	22.20
4. Anti-Terra U80	Anti-Terra U-80	Byk Chemie	3.10
5. Additive	Bentone	SD-2	11.50
6. Solvent	MIBK		15.30
7. Solvent	Xylene		45.90
8. Solvent	Dowanol PM	Dow	15.30
9. Filler	Barite		152.90
10. Filler	Talc 400 mesh		191.10
11. Filler	Quartz 400 mesh		191.10
12. Pigment	Zinc Phosphate	Heubach	30.60
13. Pigment	Bayferrox 130M	Bayer	68.70
Total A			1000.00
B-Component (g)			
1. Curing Agent	Ancamide 350A	Evonik	118.87
2. Additive	Ancamine K54	Evonik	4.99
3. Solvent	Xylene		120.01
4. Solvent	Butanol	72.03	315.90
Total A+B			1315.90

After mixing Part A and B, apply a 30 minute induction time prior to application.

TABLE 12: TECHNICAL DATA

Mixing ratio	Volume A:B	3:2	PVC	%	35.19%
			Pot-life	h	3.5
Density (g/ml)	- Mix	1.47	Gloss (60°)		17
			Hard Dry Thumb twist	h	16.00
			Epoxy/Amine		1.08
Solid Content (Weight %)	- Mix	79.55			
Solid Content (Volume %)	- Mix	64.17			

Epoxy Curing Agents and Modifiers

ANCAMIDE® 351A Curing Agent

EVONIK CORPORATION

7201 Hamilton Blvd.
Allentown, PA 18195
1 800 345-3148
Outside U.S. and Canada 1 610 481-6799

For Technical Information and Support:

Americas: picus@evonik.com
EMEA: apcse@evonik.com

Disclaimer

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.

