

AMICURE® CG-1200G Curing Agent**DESCRIPTION**

Amicure CG-1200G curing agent is a micronized grade of dicyandiamide containing 0.5% of an inert flow control additive to inhibit clumping and improve handling. It is designed for use as a latent curing agent for epoxy resins.

ADVANTAGES

- Fine particle size provides enhanced reactivity versus coarser grades
- Easily dispersed in liquid resins due to higher levels of flow agent
- Shelf stability up to 6 months at 77°F in properly formulated systems
- Activation temperature can be easily varied from 355°F to 203°F with appropriate accelerator selection

APPLICATIONS

- One-component adhesives
- Recreational and industrial pre-preg composites
- Powder coatings

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Amicure CG-1200G curing agent.

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

TYPICAL CURE SCHEDULE

- 1–2 hours at 355°F.
- 45 minutes at 250°F with 0.5 parts Imicure™ AMI-2 curing agent.
- 30 minutes at 285°F with 2–5 parts Ancamine® 2441 curing agent.

SUGGESTED ACCELERATORS

- Ancamine 2014AS curing agent
- Amicure UR/UR2T
- Imidazoles
- Ancamine 2441 curing agent

TABLE 1: TYPICAL PROPERTIES

Appearance	White, Crystalline Particles
Melt Point (°F)	405-406
Particle Size (microns)	
90%	<30
50%	<11
Nitrogen as % of Dicy	99
Equivalent Wt/{H}	21
Recommended Use Level (phr, EEW=190)	4-15

TABLE 2: TYPICAL HANDLING PROPERTIES

Gel Time (150g mass @ 77°F) (mo)	12
---	----

TABLE 3: TYPICAL PERFORMANCE

Tg (°F)*	250
Tg (°F) when accelerated with Ancamine 2441	266

* Measured using DSC with 18°F/ min ramp. Value will be higher when accelerated with an imidazole.

Epoxy Curing Agents and Modifiers

AMICURE® CG-1200G Curing Agent

EVONIK CORPORATION

7201 Hamilton Blvd.
Allentown, PA 18195
1 800 345-3148
Outside U.S. and Canada 1 610 481-6799

For Technical Information and Support:

Americas: picus@evonik.com
EMEA: apcse@evonik.com

Disclaimer

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.

