

ANCAMINE® DL50 Curing Agent**DESCRIPTION**

Ancamine DL50 curing agent is a liquid mixture of aromatic amines based on methylenedianiline (MDA). In addition to MDA, Ancamine DL50 curative contains polymethylene polyanilines and aromatic amines with a functionality greater than 4. The multifunctional nature of polymethylene polyanilines can increase the crosslink density of a completely cured epoxy compared with methylenedianiline. Ancamine DL50 curative is best suited for use as an epoxy curative in forced cure applications. This aromatic, multifunctional curative can be used to produce high-strength, chemically-resistant, elevated temperature-tolerant epoxy parts. Epoxy systems cured with Ancamine DL50 curative offer excellent resistance to water, acid, alkalies and hydrocarbon solvents.

APPLICATIONS

- Laminating and filament winding
- Composite and pre-preg fabrication
- Casting and tooling

SHELF LIFE

At least 60 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine DL50 curing agent.

TYPICAL PROPERTIES

Appearance	Yellow-to-Light-Brown
Viscosity @ 40°C [Pa.s]	30
Specific Gravity @ 25°C	1.10
Equivalent Wt/{H}	51
Recommended use Level (phr, EEW = 190)	27

TYPICAL PERFORMANCE*

Glass Transition Temperature by DSC (°C)	166
Tensile Strength [MPa]	72
Tensile Modulus, [GPa]	2.8
Elongation (%)	4.0

* Ancamine DL50 curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

TYPICAL CURE SCHEDULE

2 h at 80°C plus 3 h at 150°C

Epoxy Curing Agents and Modifiers

ANCAMINE® DL50 Curing Agent

EVONIK RESOURCE EFFICIENCY GMBH
Business Line Crosslinkers
Paul-Baumann-Straße 1
45764 Marl
Germany

apcsepx@evonik.com
www.evonik.com/crosslinkers

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

