

## VESTANAT® HT 2500

43.13.339e / 03.17

### General description

VESTANAT® HT 2500 is an aliphatic polyisocyanate based on hexamethylene diisocyanate (VESTANAT® HDI). It contains isocyanurate groups and has a functionality of 3 to 4. VESTANAT® HT 2500 is available as solvent grades as well as solvent free. Each is a low to medium viscosity liquid.

### Specification

VESTANAT® Property	HT 2500 L	HT 2500 E	HT 2500/100	HT 2500/LV	Unit	Test method
Non volatile matter	90 ± 1 <sup>1)</sup>	90 ± 1 <sup>2)</sup>	Solvent free	Solvent free	% by wt.	EN ISO 3251
NCO content	19.6 ± 0.3	19.6 ± 0.3	21.8 ± 0.3	23.0 ± 0.5	% by wt.	EN ISO 11909
Viscosity at 23 °C	550 ± 150	500 ± 150	3000 ± 750	1200 ± 300	mPas	EN ISO 3219

### Typical data

Density at 23 °C	~ 1.13	~ 1.13	~ 1.16	~ 1.16	–	EN ISO 2811
Colour (APHA)	≤ 40	≤ 40	≤ 40	≤ 40	–	EN ISO 6271
Flash point (closed cup)	~ 50	~ 50	~ 158	~ 158	°C	EN ISO 1523
VESTANAT® HDI monomer	≤ 0.15	< 0,15	< 0.15	≤ 0.25	%	EN ISO 10283

<sup>1)</sup> dissolved in n-butyl acetate / solvent naphtha 100 = 1:1; other solution grades are available on request

<sup>2)</sup> dissolved in n-butyl acetate

### Properties and Applications

VESTANAT® HT 2500 is used as a crosslinker for 2K-PUR paints based on suitable polyesters, acrylates, flexible medium-oil or short-oil alkyd resins and other OH-group containing resins. This way, polyurethane paints with outstanding weather resistance and light fastness are obtained. Blends of VESTANAT® HT 2500 with VESTANAT® T 1890 in 2K-PUR paints improve drying performance, surface hardness, pot life and chemical resistance against environmental etch.

Typical applications are automotive OEM and car repair paints, maintenance -, wood -, industrial- and plastic coatings.

VESTANAT® HT 2500 can be diluted with aromatics and esters down to a solids content of approx. 40 % by wt. Solvents for diluting VESTANAT® HT 2500 should in general be of urethane grade, i.e., the water content should be below 0.05 %. Protic solvents like alcohols or amines have to be avoided as well.

## Catalysis

The basic reactivity of VESTANAT<sup>®</sup> HT 2500 is lower compared to aromatic- and higher compared to cycloaliphatic polyisocyanates. If necessary, zinc octoate, tin- or bismuth- catalysts are recommended as a urethane catalyst.

## Storage and Packaging

VESTANAT<sup>®</sup> HT 2500 is moisture sensitive. It can be stored in unopened containers for at least 6 months at room temperature without loss of quality in accordance with the above specification.

VESTANAT<sup>®</sup> HT 2500 grades are supplied in non-returnable drums with a net weight of 225 kg each and in non-returnable plastic containers (IBC) with a net weight of 1.000 kg (except VESTANAT<sup>®</sup> HT 2500/100).

## Safety and Handling

The product is used as raw material for the industrial manufacture of resins and hardeners for coating materials, adhesives, sealants and elastomers. The handling of such materials containing reactive polyisocyanates and residual monomeric diisocyanates requires appropriate protective measures. Therefore these products may be used only in industrial or professional applications. They are not suitable for use in homemaker (DIY) applications.

Please refer to our Safety Data Sheet.

---

<b>Evonik Resource Efficiency GmbH</b>	<b>Evonik Corporation</b>	<b>Evonik Speciality Chemicals Co., Ltd.</b>
Paul-Baumann-Str. 1	Reource Efficiency	55, Chundong Road
45764 Marl	299 Jefferson Road	Xinzhuang Industry Park
Germany	Parsippany, NJ 07054-0677, USA	Shanghai, 201108, PR China
PHONE +49 2365 49-02	PHONE +1 973 929-8000	PHONE +86 21 6119-1000
FAX +49 2365 49-5030	FAX +1 973 929-8460	FAX +86 21 6119-1168
<a href="http://www.evonik.com/crosslinkers">www.evonik.com/crosslinkers</a>	<a href="http://www.evonik.com/crosslinkers">www.evonik.com/crosslinkers</a>	<a href="http://www.evonik.cn/crosslinkers">www.evonik.cn/crosslinkers</a>
<a href="http://www.evonik.com/coatings">www.evonik.com/coatings</a>	<a href="http://www.evonik.com/coatings">www.evonik.com/coatings</a>	<a href="http://www.evonik.com/coatings">www.evonik.com/coatings</a>
E-MAIL <a href="mailto:vesta@evonik.com">vesta@evonik.com</a>	E-MAIL <a href="mailto:vesta@evonik.com">vesta@evonik.com</a>	E-MAIL <a href="mailto:vesta@evonik.com">vesta@evonik.com</a>

Replaces leaflet 43.13.339e / 07.10 and all former issues  
Marl, March 2, 2017

VESTANAT<sup>®</sup> is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used