

ANCAMINE[®] AEP Curing Agent**DESCRIPTION**

Ancamine AEP curing agent is a 96% minimum purity grade of N-aminoethyl-piperazine, designed for use as a curing agent for liquid epoxy resins. It is characterized by its rapid gel at room temperature to give a B-stage cure. It requires an elevated temperature post-cure to obtain optimum properties, notably high impact strength and good thermal shock resistance. It can also be formulated with flexibilizers and accelerators to give systems that will cure at room temperature.

APPLICATIONS

- Concrete adhesives and mortars
- Trowelable flooring
- Decoupage systems
- Small electrical pottings and encapsulation
- Accelerating co-curing agent for other amines

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine AEP curing agent.

TYPICAL CURE SCHEDULE

- Gel at room temperature plus 2 hours at 212°F.

TYPICAL PROPERTIES

Appearance	Clear liquid
Color (Gardner)	1
Viscosity @ 77°F (cP)	10
Amine Value, mg KOH/g	1,297
Density @ 77°F (lb/gal)	8.2
Flash Point (closed cup) (°F)	215
Equivalent Wt/{H}	43
Recommended Use Level (phr, EEW=190)	23

TYPICAL HANDLING PROPERTIES*

Gel Time (150g mix @ 77°F) (min)	19
---	----

TYPICAL PERFORMANCE*

Heat Deflection Temperature (ASTM D648-264 psi) (°F)	225
Flexural Strength (psi)	19,000
Tensile Strength (psi)	10,000

* Ancamine AEP curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

Epoxy Curing Agents and Modifiers

ANCAMINE® AEP Curing Agent

EVONIK CORPORATION

7201 Hamilton Blvd.
Allentown, PA 18195
1 800 345-3148
Outside U.S. and Canada 1 610 481-6799

For Technical Information and Support:

Americas: picus@evonik.com
EMEA: apcse@evonik.com

Disclaimer

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.

