

DESCRIPTION

Epodil 757 reactive diluent is a technical grade of the glycidyl ether of cyclohexane dimethanol. The product is a cycloaliphatic difunctional reactive diluent used to reduce the viscosity of epoxy resin systems.

ADVANTAGES

- Excellent creep resistance
- Good maintenance of physical properties
- Moderate dilution efficiency
- Minimal effect on cure speed

APPLICATIONS

- Laminates
- Potting compounds
- Mortars, grouts and flooring

SHELF LIFE

At least 36 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Epodil 757 reactive diluent.

TABLE 1: TYPICAL PROPERTIES

Appearance	Clear Liquid
Color (Gardner)	2
Viscosity @ 77 °F (25 °C) (cP)	65
Specific Gravity @ 77 °F (25 °C)	1.10
Flash Point (Setaflash) (°F)	>200
Hydrolyzable Chloride (max)	.02
Residual Epichlorohydrin (ppm max)	10
Weight per Gallon (lb/gal)	9.2
Moisture Content (% max)	0.2
Equivalent Wt/{H}	166
Recommended Use Level See Table	See Table

TABLE 2: SUPPLEMENTARY DATA

Epodil 757 reactive diluent can be used as follows to lower the viscosity of a standard Bisphenol-A liquid epoxy resin (EEW=190) with an initial viscosity of 12,500 cP:

Weight Percent Epodil 757 (%)	Viscosity @ 77°F (25°C)(cP)
10	4,800
20	1,950
30	1,000

EXAMPLE IMPACT OF DILUENT ON A SIMPLE FORMULATED SYSTEM

Evonik recommends that the formulator test reactive diluents in their system for performance. The following data is provided as an example of the impact of the reactive diluent on a simple formulated system.

SYSTEM:

- BADGE with 12.5 wt% Epodil 757
- Cured with Ancamine® 1618 curing agent at 1:1 stoichiometry

Property	Without Epodil 757	With Epodil 757
Persoz hardness² at 23°C (1 day/7day)	195/310	109/292
Phase 3 dry time³ (h)	7:10	8:24
Tg⁴ (1st scan)	51	51
Gel time⁵ (min)	55	53

- (2) BYK Persoz pendulum tester according to ISO 1522 with 10 mil WFT at 23°C/50% RH
- (3) 6 mil WFT BK Drying time recorder according to ASTM D5895 with 6 mil WFT at 23°C/50% RH
- (4) TA Instruments DSC model Q200 first scan data
- (5) 150g mix using TECHNE Gel-timer

Epoxy Curing Agents and Modifiers

EPODIL[®] 757 Reactive Diluent

EVONIK CORPORATION

7201 Hamilton Blvd.
Allentown, PA 18195
1 800 345-3148
Outside U.S. and Canada 1 610 481-6799

For Technical Information and Support:

Americas: picus@evonik.com
EMEA: apcse@evonik.com

Disclaimer

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.

