

ANCAMINE® TEPA Curing Agent**DESCRIPTION**

Ancamine TEPA curing agent is a standard commercial grade of tetraethylene pentamine. It is less corrosive and has a lower vapor pressure than either Ancamine DETA or TETA curing agents, and is also less hygroscopic and less prone to carbamation.

ADVANTAGES

Extended pot life and less tendency to blush compared with other unmodified aliphatic amines.

APPLICATIONS

- Solvent-based baked coatings
- Encapsulation

SHELF LIFE

At least 18 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet on Ancamine TEPA curing agent.

TYPICAL CURE SCHEDULE

- 2–7 days at room temperature.
- Gel at room temperature plus 2 h at 212°F.

TABLE 1: TYPICAL PROPERTIES

Appearance	Clear Amber Liquid
Color (Gardner)	2
Viscosity @ 77°F (cP)	80
Density @ 77°F (lb/gal)	8.3
Flash Point (closed cup) (°F)	365
Equivalent Wt/{H}	31
Recommended Use Level (phr, EEW=190)	16

TABLE 2: TYPICAL HANDLING PROPERTIES

Gel Time (150g mix @ 77°F) (min)	35
---	----

Epoxy Curing Agents and Modifiers

ANCAMINE® TEPA Curing Agent

EVONIK CORPORATION

7201 Hamilton Blvd.
Allentown, PA 18195
1 800 345-3148
Outside U.S. and Canada 1 610 481-6799

For Technical Information and Support:

Americas: picus@evonik.com
EMEA: apcse@evonik.com

Disclaimer

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.

