

Sunmide[®] 307D-60 Curing Agent

DESCRIPTION

Sunmide 307D-60 is a polyamide amine in xylene and n-butanol. It displays very good thixotropic properties. Sunmide 307D-60 is most commonly used for fast cure and fast dry applications for industrial epoxy coatings.

ADVANTAGES

- Fast cure
- Low toxicity
- Long pot life

APPLICATIONS

- General epoxy coatings
- Zinc rich paints
- Adhesive for abrasive paper

SHELF LIFE

- Stable under temperate or tropical conditions.
- Recommended shelf life – 1 year

STORAGE AND HANDLING

Refer to the Safety Data sheet for Sunmide 307D-60 curing agent.

TYPICAL PROPERTIES

| | |
|----------------------------------|------------------------------|
| Amine Value (mg KOH/g) | 120-140 |
| Color (Gardner) | 12 max |
| Viscosity (mPa.s at 25°C) | 2000-4000 |
| Non Volatile (%) | 58-62 |
| Specific Gravity | 0.93 |
| Solvent | Xylene / n-butanol (8/2) |
| Equivalent Wt/{H} | 226 (solid) / 377 (solution) |

Epoxy Curing Agents and Modifiers

Sunmide® 307D-60 Curing Agent

EVONIK CORPORATION

7201 Hamilton Blvd.
Allentown, PA 18195
1 800 345-3148
Outside U.S. and Canada 1 610 481-6799

For Technical Information and Support:

Americas: picus@evonik.com
EMEA: apcse@evonik.com

Disclaimer

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.

