

# Ancamide<sup>®</sup> 351A Curing Agent

## DESCRIPTION

Ancamide 351A curing agent is a member of a new series of reactive polyamides developed for use in the curing of epoxy resins in coatings and adhesives applications. Special features include good colour, colour stability, excellent corrosion resistance and superior adhesion properties. It is freely compatible with a wide range of solvents, including those generally used in epoxy resin based coatings.

## ADVANTAGES

- Good corrosion resistance
- Excellent adhesion to a variety of substrates
- Good colour and light stability
- Compatible with wide range of solvents

## APPLICATIONS

- Structural adhesives
- Solvent based marine and protective coatings
- Primers, sealers and coatings for concrete

## SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

## PACKAGING AND HANDLING

Refer to the Safety Data Sheet for Ancamide 351A curing agent.

## TYPICAL PROPERTIES

<b>Appearance</b>	Clear Amber Liquid
<b>Colour<sup>1</sup> (Gardner)</b>	8 max
<b>Viscosity<sup>2</sup> @ 25°C, [mPa.s]</b>	10,000-20,000
<b>Amine Value<sup>3</sup> (mg KOH/g)</b>	370±20
<b>Specific Gravity @ 21°C</b>	0.97
<b>Equivalent Wt {active N-H}</b>	100
<b>Recommended use Level<sup>4</sup> [PHR]</b>	50-55
<b>Solids Content, [%]</b>	100

## TYPICAL HANDLING PROPERTIES [@ 50 PHR]<sup>4</sup>

<b>Gel Time<sup>5</sup> [mins]</b>	150
<b>Thin Film Set Time<sup>6</sup> 25°C, [h]</b>	10

## TYPICAL CURE SCHEDULE

**2-7 Days at Room Temperature**

## FILM PROPERTIES AFTER 10 DAYS CURE @ 23°C

<b>Direct impact [cm.kg]</b>	40
<b>Reverse impact [cm.kg]</b>	10
<b>Flexibility Cylindrical Mandrel<sup>7</sup> (mm pass)</b>	3

Footnotes:

- (1) ASTM D 1544-80
- (2) Brookfield RVTD, Spindle 4
- (3) Perchloric Acid Titration
- (4) With Bisphenol A diglycidyl ether (EEW=190)
- (5) 150 gms mixed mass @ 25°C
- (6) BK Drying Recorder Phase II
- (7) Erichsen mandrel tester 266

## STRUCTURAL ADHESIVES APPLICATIONS

### SUPPLEMENTARY INFORMATION

Ancamide 351A curing agent is medium viscosity polyamide, supplied at 100% solids. The product is intended for use in combination with or without other amine curing agent in two part room temperature or heat cured adhesives formulations. When used with a standard DGEBA type liquid epoxy resin (EEW=190) Ancamide 351A curing agent offers excellent handling and physical properties and adhesion to various substrates.

Ancamide 351A curing agent has a non-critical loading and can be used at levels ranging from 40 to 70 phr with the preferred range being 50-60 phr with a standard DGEBA type liquid epoxy resin.

### PHYSICAL PROPERTIES

Physical properties of Ancamide 351A curing agent cured standard liquid epoxy resin was compared with Ancamide 350A curing agent cured epoxy after seven days ambient temperature cure and after a 30 minutes cure @120°C. The tensile data after seven days ambient cure schedule shows that Ancamide 351A curing agent cured epoxy resin offers greater than 30% higher tensile strength and greater than 80% higher tensile elongation without any adverse effect on tensile modulus. This behavior indicates that Ancamide 351A curing agent provides inherent toughness to the cured epoxy resin.

The tensile data after heat cure schedule shows that Ancamide 351A curing agent demonstrated more than 25% increase in tensile elongation as compared to Ancamide 350A curing agent without any adverse impact on tensile strength. In addition, increased elongation is observed without significant reduction in glass transition temperature.

**TABLE 1: PHYSICAL PROPERTIES**

	Ancamide 350A	Ancamide 351A
DGEBA liquid epoxy resin	100	100
Ancamide 350A	55	0
<b>Ancamide 351A</b>	<b>0</b>	<b>55</b>
<b>After 7 Days RT Cure</b>		
Tensile Strength, psi	6400	8600
Tensile elongation at failure, %	1.8	3.4
Tensile Modulus, ksi	407	412
Tg, C	50	50
<b>After 30 minutes @ 120°C Cure</b>		
Tensile Strength, psi	8500	8300
Tensile elongation at failure, %	5.5	7.0
Tensile Modulus, ksi	364	342
Tg, C	100	96

### STARTING POINT FORMULATION

A two-part model formulation (Appendix 1) was prepared using Ancamide 351A curing agent as a main curative. Ancamine 2641 curing agent, a modified amine, was used as a co-curing agent along with Ancamide 351A curing agent. Typical fillers and additives were used in the same formulation. A control formulation was prepared using Ancamide 350A curing agent.

Epoxy portion and a curative portion were mixed together based on theoretical EEW of epoxy portion and AHEW of a curative using 1:1 stoichiometric ratio. The mixed adhesive system was used to make single lap shear samples and peel samples for further testing. Substrates used were cold rolled steel (CRS), ABS and polycarbonate. All substrates were used without any surface treatment prior to bonding.

For CRS lap shear samples, 0.5" overlap was used whereas for ABS and polycarbonate substrates 1.0" overlap was used. Only CRS substrate was used to prepare peel samples. In all cases 10 mils bondline thickness was maintained using 10 mils diameter glass beads.

All samples were cured following two cure schedules, (1) seven days ambient temperature cure or (2) 30 minutes at 120°C cure. The samples were tested at ambient temperature following standard test methods.

### PERFORMANCE EVALUATION

**TABLE 1: PHYSICAL PROPERTIES**

	Ancamide 351A based B component	Ancamide 350A based B component Control
<b>7 days @ 25°C cure</b>		
CRS/CRS shear strength, psi	1800	1700
ABS/ABS shear strength, psi	520	360
Polycarbonate/Polycarbonate Shear strength, psi	230	250
CRS/CRS peel strength, pli	10.5	9.8
<b>30 minutes @ 120°C cure</b>		
CRS/CRS shear strength, psi	2000	2050
CRS/CRS peel strength, pli	14.0	13.5

**Lap shear Strength:** After room temp cure and after heat cure schedules, formulation based on Ancamide 351A curing agent demonstrated performance very similar or slightly higher than the formulation based on Ancamide 350A curing agent. The mode of failure for CRS was 100% cohesive and adhesive for thermoplastic substrates.

**Peel Strength:** After both cure schedules, Ancamide 351A curing agent based formulation exhibited little higher peel strength compared to the Ancamide 350A curing agent based formulation. In both cases, the mode of failure was cohesive.

## SOLVENT BASED MARINE AND PROTECTIVE COATINGS APPLICATION

### FILM PROPERTIES

In a clear coat formulation Ancamide 351A curing agent also exhibits a good degree of flexibility. As shown in Table 3, the direct impact resistance of Ancamide 351A curing agent is comparable to Ancamide 350A curing agent. Ancamide 351A curing agent formulations can also be accelerated using Ancamine® K54 (phenolic, tertiary amine accelerator). Levels can be varied to achieve the desired dry speed properties, with the preferred level in the 2.5-5.0% range based on Ancamide 351A use level.

**TABLE 3: CLEAR COAT PERFORMANCE PROPERTIES**

Property	Ancamide 351A(*)	Ancamide 350A(*)
Direct Impact	40	40
Reverse Impact	10	10
Dry Speed BK Phase II [h]	9:30	10:00
Dry Speed (+2.5% K54)	5:00	5:30
Specular Gloss 60°	90	95
Cross Hatch Adhesion (dry)	Gt0	Gt0

(\*) Ancamide 351A and Ancamide 350A tested with liquid Bis A diglycidyl ether (EEW 190), Cross hatch adhesion Gt0 = no loss of adhesion.

### STARTING POINT FORMULATIONS

Appendix 2 contains an anti-corrosive primer formulation based on Ancamide 351A. As with all solvent based coatings, dry times are influenced by solvent choice, so dry times may vary depending upon the ratio of polar and non-polar solvents incorporated into the coating formulation. Pot lives as measured by the time for the mix to double in viscosity are in the 3-6 hours range, which is typical for such solvent based polyamide systems.

Formulation A351A-1, with Liquid Epoxy Resin, is 64% volume solids. PVC is 35% for both formulations. The primer formulation is compatible with a variety of different let down solvents (including xylene, n-butanol, MIBK, methoxy-propanol, etc) and can be further let down if required for additional spray applications. The coating formulation can be applied with conventional spray equipment or brush applied to the steel substrate.

Formulation A351A-1 was evaluated for corrosion resistance properties using salt spray, Distilled Water Immersion and NaCl 3.5% immersion at room temperature. After 1000 h exposure, coatings exhibit excellent corrosion resistance. No signs of field blisters have been detected using the above tests, with panels exhibiting no scribe creep in the salt spray test. For comparative purposes, Ancamide 350A curing agent was also included in the test study as the "industry" standard reference. In all the corrosion resistance tests carried out, both Ancamide 351A and Ancamide 350A curing agents demonstrated comparable performance.

### PERFORMANCE EVALUATION

Formulation A351A-1 was evaluated in 5% salt spray, distilled water immersion at room temperature and NaCl 3.5% immersion at room temperature, following a 10 day ambient cure of applied coatings.

Coatings were applied to grit blasted, hot rolled steel (SA2.5), using conventional spray equipment, in double coats to give coatings with a 75-100µ dry film thickness (DFT). In salt spray, (ASTM B-117) panels were scribed and evaluated for field blisters using the US Federal Standard Test Method 141a, Method 6461 and the scribe creep was rated in accordance with ASTM D-1654. Similar evaluations were made for panels placed in NaCl 3.5% immersion at room temperature and distilled water immersion. Panels exposed to distilled water immersion were not scribed and coatings were assessed for blistering only. These tests also included evaluations for changes in visual appearance.

### CORROSION RESISTANCE

Anti-corrosive primers based on Ancamide 351A and Ancamide 350A curing agents were evaluated for salt spray, distilled water and NaCl 3.5% immersion at room temperature. The results obtained are presented in Table 4, 5 and 6. After 1000hrs salt fog exposure, formulations with Ancamide 351A curing agent or Ancamide 350A curing agent exhibit excellent resistance. Both formulations also demonstrated excellent water and salt water resistance with no signs of field blistering being observed following 1,000 h continuous testing.

**TABLE 4: SALT SPRAY RESISTANCE — ANCAMIDE 351A AND ANCAMIDE 350A [1000H]**

	Ancamide 351A	Ancamide 350A
Overall rating	9-10	9-10
Scribe creep	0-1mm	0-1mm
X-hatch adhesion after 1,000 h	5B	5B

5% salt spray, cabinet temperature 35°C - ASTM B-117, film thickness 75-100µ; Rating: 10 = Best (no blisters), 0 = Worst

**TABLE 5: DISTILLED WATER IMMERSION @ RT — ANCAMIDE 351A AND ANCAMIDE 350A [1000H]**

	Ancamide 351A		Ancamide 350A	
	Before immersion	After 1,000 h	Before immersion	After 1,000 h
X-Hatch Adhesion	5B	5B	5B	5B
Gloss/Appearance	No change	No change	No change	No change

**TABLE 6: NaCl 3.5% IMMERSION @ RT — ANCAMIDE 351A AND ANCAMIDE 350A [1000H]**

	Ancamide 351A		Ancamide 350A	
	Before immersion	After 1,000 h	Before immersion	After 1,000 h
X-Hatch Adhesion	5B	5B	5B	5B
Gloss/Appearance	No change	No change	No change	No change
Scribe creep	0 mm	0 mm	0 mm	0 mm

## APPENDIX 1

### ANCAMIDE 351A CURING AGENT: TWO-PART ADHESIVE FORMULATION

<b>A-Component (g)</b>			
1. Epoxy resin	DER 331	Olin	60
2. Filler	Microtuff AG 445	Speciality Minerals	38
3. Additive	Cab-O-Sil TS 720	Cabot Industries	2
<b>TOTAL A</b>			<b>100</b>
<b>A-Component Manufacture Procedure:</b> Charge components 1-3 and stir homogeneous at medium to high shear			
<b>B-Component (g) Control</b>			
1. Curing agent	Ancamide 350A	Evonik	40
2. Curing agent	Ancamine 2641	Evonik	10
3. Filler	Microtuff AG 445	Speciality Minerals	22
4. Filler	Toyal 101 Aluminium powder	Toyal-America	27
5. Additive	Cab-O-Sil TS 720	Cabot Industries	1
<b>TOTAL B</b>			<b>100</b>
<b>B-Component (g) Ancamide 351A</b>			
1. Curing agent	Ancamide 351A	Evonik	40
2. Curing agent	Ancamine 2641	Evonik	10
3. Filler	Microtuff AG 445	Speciality Minerals	22
4. Filler	Toyal 101 Aluminium powder	Toyal-America	27
5. Additive	Cab-O-Sil TS 720	Cabot Industries	1
<b>TOTAL B</b>			<b>100</b>
<b>B-Component Manufacture Procedure:</b> Charge components 1-5 and stir homogeneous at medium to high shear			

## TECHNICAL DATA

EEW of A Component	317
AHEW of B Components	201
Mixing ratio (by weight)	100 of A : 63 of B
Solid content wt. (%)	100

## APPENDIX 2

### FORMULATION A351-1: ANCAMIDE 351A CURING AGENT ANTI-CORROSIVE PRIMER FORMULATION

			Anti-Corrosive Primer
<b>A-Component (g)</b>			
1. Epoxy Resin	DER 331	Olin	229.40
2. Diluent	Epodil LV5	Evonik	22.90
3. Diluent	Epodil 748	Evonik	22.20
4. Anti-Terra U80	Anti-Terra U-80	Byk Chemie	3.10
5. Additive	Bentone SD-2		11.50
6. Solvent	MIBK		15.30
7. Solvent	Xylene		45.90
8. Solvent	Dowanol PM	Dow	15.30
9. Filler	Barite		152.90
10. Filler	Talc 400 mesh		191.10
11. Filler	Quartz 400 mesh		191.10
12. Pigment	Zinc Phosphate	Heubach	30.60
13. Pigment	Bayferrox 130M	Bayer	68.70
<b>TOTAL A</b>			<b>1000.00</b>
<b>B-Component (g)</b>			
1. Curing Agent	Ancamide 351A	Evonik	118.87
2. Additive	Ancamine K54	Evonik	4.99
3. Solvent	Xylene		120.01
4. Solvent	Butanol		72.03
			<b>315.90</b>
<b>TOTAL A+B</b>			<b>1315.90</b>
After mixing Part A and B, apply a 30 minute induction time prior to application.			

## TECHNICAL DATA

Mixing ratio	Volume A:B	3:2	PVC	%	35.19%
			Pot-life (h)	h	3.5
Density (g/ml)	- Mix	1.47	Gloss (60°)		17
			Hard Dry Thumb twist	h	16.00
			Epoxy/Amine		1.08
Solid Content (Weight %)	- Mix	79.55			
Solid Content (Volume %)	- Mix	64.17			

## SALT SPRAY PANELS 1000H EXPOSURE



## NaCl 3.5% IMMERSION @ ROOM TEMPERATURE 1000H EXPOSURE



**EVONIK RESOURCE EFFICIENCY GMBH**  
Paul-Baumann-Straße 1  
45772 Marl, Germany  
+31.30.2857100  
[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**For Technical Information, Support and Samples:**  
[apcsepx@evonik.com](mailto:apcsepx@evonik.com)

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

