

ANCAMINE® 2712M Curing Agent**DESCRIPTION**

Ancamine 2712M curing agent is a modified polyamine curing agent intended for use as a curing agent for diluted liquid epoxy resin at ambient and low temperature application (10°C).

Ancamine 2712M curing agent is free of benzyl alcohol, facilitating zero volatile organic component coating and flooring formulations. Also, Ancamine 2712M curing agent allows the use in low emission coating and flooring systems.

ADVANTAGES

- Fast cure and development of properties at ambient and low temperature
- High resistance to carbamation and water spotting
- High mechanical and chemical resistances
- Free of benzyl alcohol

APPLICATIONS

- Low emission coatings and flooring systems
- Chemically resistant, high solid and solvent-free coatings
- Industrial flooring applications

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2712M curing agent.

TABLE 1: TYPICAL PROPERTIES

Appearance	Yellow liquid
Color (Gardner)¹	max 7
Viscosity @ 77°F (25°C) [mPa.s]²	350-650
Specific Gravity	1.0
Amine Value (mg KOH/g)³	500-560
Equivalent Wt/{H}	95
Recommended use Level, [PHR]⁴	50

TABLE 2: TYPICAL HANDLING PROPERTIES⁵

Use Level, [PHR]	50
Viscosity @ 74°F (23°C) [mPa.s]²	800-900
Gel Time, (150g mix at 77°F) (23°C) [min]⁶	30-35
Thin Film Set Time 23°C [h]⁷	7.0
Gloss 20°/60°, 23°C	105/102
PersoZ Pendulum Hardn. 23°C, d1/d7 [s]⁸	240/360
Hardness 23°C, 16h/d7 [Shore D]⁹	80D/85D
Carbamation Resist. 23°C, 24h [Scale 1-5]¹⁰	5
Thin Film Set Time 50°F (10°C), [h]⁷	14.0
Gloss 20°/60°, 10°C	105/102
PersoZ Pendulum Hardn. 10°C, d2/d7 [s]⁸	135/375
Hardness 10°C, 24h/d7 [Shore D]⁹	65D/85D
Carbamation Resist. 10°C, 2d [Scale 1-5]¹⁰	4

Footnotes:

- (1) ASTM D 1544-80
- (2) Brookfield DV+ Spindle 5
- (3) Perchloric Acid Titration
- (4) With Bisphenol-A diglycidyl ether (EEW=190)
- (5) With Bisphenol A/F diglycidyl ether blend, Epodil® 748 reactive diluent diluted, EEW195, η 900 mPa.s
- (6) Techne GT-3 Gelation Timer
- (7) ASTM D5895 BK Drying Recorder Phase III
- (8) ISO 1522
- (9) ISO 868
- (10) ISO 2812 (Wet Patch Method), scale 1-5 (5 is best)

Epoxy Curing Agents and Modifiers

ANCAMINE[®] 2712M Curing Agent

EVONIK CORPORATION

7201 Hamilton Blvd.
Allentown, PA 18195
1 800 345-3148
Outside U.S. and Canada 1 610 481-6799

For Technical Information and Support:

Americas: picus@evonik.com
EMEA: apcse@evonik.com

Disclaimer

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.

